


DARVOLEX[®]

A new feeling of wood

DECKING CHARACTERISTICS

Characteristic	Unit	Reference
Profile Hight 	26 mm	EN 13986:2004 EN 14342:2005+A1:2008
Thikness Swelling for 24 hours	<0.50%	
Flexural Moduls	>6000MPa	
Flexural Strength	>35MPa	
Slip resistance	USRV 35	
Classification with regard to fire reaction	E _{fl}	
Formaldehyde release	E ₁	
Quantitative determination of pentachlorophenol in wood	<1ppm	

The tests are made in accordance with DD CEN/ TS 15534-1:2007 and the internal factory criteria of Transplast MPD Ltd.- Plovdiv